



PRODUCT INFORMATION

PLANKS	Thickness	6.5 mm (≈ 1/4 in)
	Dimensions	9 x 60 in (220 x 1,515 mm)
	Wear Layer	20 mil (≈ 0.5 mm) Ceramic Bead Coating
	Finish	NatuReal® Low Gloss Matte
	Texture	Realistic TexTrue® Emboss in Register (EIR)
	Plank Edges	4-Sided Painted V-Groove
	Locking System	Patented Drop n' Lock 5G® by Välinge

CARTONS	Planks	5 planks
	Coverage	17.94 sq ft (≈ 1.666 sq m)
	Dimensions	9.5 x 60.5 x 1.5 in (W x L x H)
	Weight	27.80 lbs (≈ 12.60 kg)

PALLETS	Boxes	60 boxes
	Coverage	1,076.39 sq ft (≈ 141.18 sq m)
	Dimensions	38 x 61 x 38 in (W x L x H)
	Weight	1,750 lbs (≈ 800 kg)

INSTALLATION	Floating (Recommended)	2 mm Closed-Cell Foam Underlayment 1.5 mm or thicker Cork Underlayment
	Glue-Down	Suitable *
	Sanctioned Sub-Floors	Concrete (Leveled and free of cracks) ** Wood (Leveled and properly fastened) ** Radiant Heated Concrete (Turn off for installation) **
	Can Be Installed Over	Ceramic and Porcelain Tiles * Glue-down or Nailed Down Hardwood Floors * Glue-down LVT or LVP *
	Suitable Levels	On, Above, or Below Grade

* Refer to the adhesive manufacturer's guidelines for approved substrates and compatibility.

** Learn more about approved substrates and radiant heating sub-floors on the installation guidelines

TECHNICAL SPECIFICATIONS

TECHNICAL CLASSIFICATION	STANDARD	RESULT
Type of Floor Covering	EN ISO 10582	Compact Resilient Flooring
CE Certification	EN 14041	YES
Classification	EN ISO 10874	Residential: 21
		Commercial: 32
		Industrial: 42

TECHNICAL PERFORMANCE	STANDARD	RESULT
Dimension Stability	EN ISO 23999	≤ 0.10 %
Reaction to Fire	EN 13501-1	Bfl s1 on concrete sub-floor Cfl s1 on wood sub-floor
Residual Indentation	EN ISO 24343-1	≤ 0.05 mm
Furniture Leg	EN 424	No Damage
Castor Chair	EN ISO 4918	No Damage
Curl Resultant to Heat	EN ISO 23999	≤ 2 mm
Underfloor Radiant Heating	EN ISO 10456	Suitable – Max. 27°C *
Thermal Resistance	ISO 10456	0.03 m ² K/W
Impact Sound Reduction	EN ISO EN 717-2	ΔL _w = 2 dB
Sound Transmission Reduction	NF EN ISO 31-074	Class C (L _{n,e,w} < 85dB)
Light Fastness	EN ISO 105-B02	≥ 6
Chemical Resistance	EN ISO 26987	High resistance
Slip Resistance	EN 13893	μ ≥ 0.30
	DIN 51130	R9
Electrical Properties	EN 1015	≤ 2kV on concrete
	EN 1081	> 109 Ω
Adhesion Wear Layer	EN 431	≥ 50N / 50mm

* Refer to the adhesive manufacturer's guidelines for approved substrates and compatibility.

** Learn more about approved substrates and radiant heating sub-floors on the installation guidelines